

Chemical Containment.

501 CRSG.

SITUATION:

Bund area required coating to protect from various potential chemical spills.

SOLUTION:

Repair damaged sections with 570 Concrete Patch Repair XF.

Prime with 503SPEP.

Protect with 2 coats of 501CRSG.

APPLICATION DETAILS:

Remove all oil and contaminants using appropriate detergents and clean water pressure wash, allow to dry.

Abrade the surface using mechanical grinders, fill and repair all damaged sections with 570 Concrete Patch Repair XF.

Prime with 503SPEP applied by brush and roller at 150 microns dft.

Stripe coat all corners and edges with 250 microns of 501 CRSG, then overcoat the entire bund area with 2 coats of 501 CRSG at a minimum of 250 microns per coat.

